



Linea : Royal Decoration
Famiglia : Bicomponenti



Prodotto: SMALT-X

DESCRIZIONE

Smalto universale 2K di altissima qualità ed elevata brillantezza. Formulato per rinnovare superfici difficili in interni ed esterni. Dotato di un'ottima adesione su ogni supporto (piastrelle, ceramica, gres, melamminico, alluminio, lamiera zincata, ferro, plastica) senza dover applicare alcun fondo. SMALT-X è inoltre un prodotto di estrema durezza e resistenza agli urti. E' pertanto possibile utilizzare il prodotto per rinnovare gli ambienti di casa, come cucine e bagni, e anche supporti destinati all'esterno.

CARATTERISTICHE PRINCIPALI

- Ottima adesione su ogni superficie.
- Estrema durezza e resistenza all'abrasione.
- Ottima brillantezza.

IMPIEGO

Metallo (ferro/leghe e lamiera zincata), legno, muratura, plastica (escluso PE e PPE). Può essere applicato su manufatti destinati all'esposizione in ambiente cittadino, rurale, costiero ed industriale di media aggressività.

APPLICAZIONE

La superficie da verniciare con SMALT-X deve essere preparata con trattamento idoneo, e precisamente:

SU SUPPORTI NUOVI: per un miglior ancoraggio e per una maggiore durata nel tempo, la superficie deve essere accuratamente sgrassata con acqua e sapone o diluente da lavaggio. Carteggiare ed applicare una o più mani di prodotto a distanza di minimo 12 ore l'una dall'altra intervallate da una leggera carteggiatura.

SU SUPPORTI GIÀ VERNICIATI: qualora lo strato di vernice preesistente non ne consigli la completa asportazione, sgrassare con acqua e detersivo, risciacquare. Se le vernici preesistenti sono in fase di distacco spazzolare e carteggiare a fondo queste parti, oppure procedere alla sverniciatura con sverniciatore. Lavare con diluente da lavaggio, o con acqua e sapone quindi applicare una o più mani di prodotto intervallate da leggera carteggiatura.

Applicazioni consigliate: a pennello, rullo, ad immersione, a spruzzo, airless.

Condizioni dell'ambiente e del supporto :

Il supporto deve essere asciutto, privo di polvere, di unto e di ogni altra sostanza inquinante

TIXE srl
Via Carlo Ferrari, 49
(Frazione Pratalborato)
15060 Capriata d'Orba (AL) IT
Phone +39 0143 46397



www.tixepaint.com
mail@tixepaint.com
Partita IVA IT 01779800992



Temperatura dell'ambiente: min. 10°C / max 35°C

Umidità relativa dell'ambiente: < 75%

Temperatura del supporto : min. 10°C / max 35°C

PREPARAZIONE DILUIZIONE

Versare tutto il contenuto del componente B (induritore) nel contenitore del componente A (smalto) e mescolare sino a completa omogeneizzazione. Utilizzare la miscela entro le 6 ore dalla preparazione.

Prodotto pronto all'uso per applicazione a rullo, e diluibile con diluente nitro o universale per bicomponenti per altri tipi di applicazione.

STOCCAGGIO

In ambiente fresco e ben ventilato.

Conservare il barattolo ben chiuso, capovolto e al riparo dal gelo e da fonti di calore.

CARATTERISTICHE FISICHE

(a 20 °C e 50% - 60%
U.R.)

Peso specifico	1,15 ± 0.02 Kg./Lt. smalto altri colori 1.20 ± 0.05 Kg./Lt.
Resa (*)	10 Mq./litro
Tempo di deflusso	30±3+Tazza ISO 2
Essiccazione	5 ore fuori impronta 18 ore in profondità 5 giorni per la massima durezza
Vita di stoccaggio	Almeno 36 mesi

Il prodotto è disponibile nelle tonalità: vedere cartella colori.

(*) La resa dipende dalla natura e dalla porosità della superficie.

CONFEZIONI

Totale A+B 500 ml

CLASSIFICAZIONE VOC

Pitture bicomponenti ad alte prestazioni. Valore UE limite per questo prodotto (Cat.A) COV 500g/l (2010). Questo prodotto contiene max 500g/l di COV.

PRECAUZIONI

Oltre alle segnalazioni di rischio e precauzione che regolano SMALT-X nella forma di produzione e che sono riportate sul contenitore, si consiglia, prima di effettuare l'applicazione del prodotto, di consultare la relativa SCHEDA DI SICUREZZA.

Eq comunque buona norma impiegare guanti ed occhiali di protezione, ed effettuare l'applicazione in ambiente ben aerato.

TIXE srl
Via Carlo Ferrari, 49
(Frazione Pratalborato)
15060 Capriata d'Orba (AL) IT
Phone +39 0143 46397



www.tixepaint.com
mail@tixepaint.com
Partita IVA IT 01779800992



Product Line : Royal Decoration
Family : Two component products



Product: SMALT-X

DESCRIPTION

Universal enamel 2k high quality and high gloss. Formulated to renew difficult surfaces both indoors and outdoors. Offering excellent adhesion on each media (tiles, ceramic, porcelain, melamine, aluminium, sheet metal, zinc, iron, plastic) without having to apply any funds. SMALT-X is also a product of extreme hardness and impact resistance. It is therefore possible use the product to renew the home environment, such us kitchens and bathrooms, and also supports for the outside.

MAIN FEATURES

- Excellent adhesion on any surface.
- Extreme hardness and abrasion resistance.
- High gloss.

USE

Metal (iron / alloys and galvanized steel), wood, masonry, plastics (except PE and PPE). Can be used on handmade package intended in urban environment, rural, coastal and industrial media aggression.

APPLICATION

The surface to be coated with SMALT-X must be prepared with appropriate treatment, namely:

ON NEW MEDIA: For a better anchorage and greater length in time, the area must be thoroughly defatted with water and soap or diluter wash. Sand and apply one or more hands of product distance minimum of 12 hours of each other interspersed by a light sanding.

MEDIA ALREADY ON 'Paint: if the existing layer of paint does not recommendations to the complete removal, degreasing with water and detergent and rinse. If the existing paint is in the process of posting brushing and sanding to the bottom these parts, or to paint stripping with paint strippers. Wash with diluter by washing with water or soap and then apply one or more hands intervals produced by light sanding.

Recommended applications: a brush, roller, dipping, spraying, airless.

Conditions and media:

The support must be dry, dust-free and grease and any other substance pollutant.

Temperature: min. 10 ° C / max 35 ° C

Relative humidity of <75%

Temperature of medium: min. 10 ° C / max 35 ° C

TIXE srl
Via Carlo Ferrari, 49
(Frazione Pratalborato)
15060 Capriata d'Orba (AL) IT
Phone +39 0143 46397



www.tixepaint.com
mail@tixepaint.com
Partita IVA IT 01779800992



PREPARATION

Pour the entire contents of component B (hardener) into the container of component A (enamel) and stir until complete homogenization. Use the mixture within 6 hour of preparation. Ready to use for roller application, and can be diluted with nitro or universal thinner for two component for other types of applications.

STORAGE

In a cool and well ventilated. Keep the jar tightly closed, upside down and away from fros and heat.

PHYSICAL CHARACTERISTICS (at 20 ° C and 50% - 60% RH)

1.15 Kg./Lt. ± Specific gravity 0:02

Yield (*) 10 Mq./L

3 "Cup 2 ISO±Time of outflow 30

5 hours drying off mark
18 hours in depth
5 days maximum hardness

Shelf life at least 36 months

The product is available in shades: See color card.

(*) The yield depends on the nature and porosity of the surface.

COLORS

See color card

PACKAGING

Total A + B 500ml

CLASSIFICATION VOC

Two-pack performance coatings. EU limit value for this product (Cat.A) VOC 500g / (2010).This product contains max 500 g / l VOC.

PRECAUTIONS

In addition to reports of the risk and precautions governing Restoring in the form o production and which are listed on the container, you should, before making the applicator of the product, see its data sheet. It 'still a good idea to use gloves and goggles, and make the application in a well ventilated.