



Quality Management System certified ISO 9001:2015 by Intertek

Prodotto da: **TIXE srl** - 15060 CAPRIATA D'ORBA (AL) ITALY  
Via C. Ferrari, 49 (Frazione Pratalborato) - T. +39 0143 46397  
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992  
**MADE IN ITALY - UN 1263 PAINT**



## Famiglia: DECORATIVI



## Prodotto: OPACUM ULTRAMATT

### DESCRIZIONE

Smalto decorativo all'acqua da interno ad elevata opacità e altamente pulibile.

### CARATTERISTICHE PRINCIPALI

- Elevata opacità
- Ottima lavabilità
- Ottima copertura
- Facile impiego
- Vasta gamma cromatica

### IMPIEGO

Smalto decorativo all'acqua ad elevata opacità, ideato per la valorizzazione degli arredi e la personalizzazione di ambienti interni secondo gli stili e le tendenze più moderne. La finitura altamente opaca conferisce aspetto uniforme ed elegante, ma al tempo stesso ottima lavabilità e possibilità di pulizia, per cui anche locali particolarmente sottoposti a frequentazione e che necessitano di sovente pulizia, possono fregiarsi di finiture a bassissima riflessione di luce.

La copertura molto spinta di OPACUM ULTRAMATT e la possibilità di colorazione nelle più svariate cromie, consentono l'impiego sulle più svariate tipologie di superficie. OPACUM ULTRAMATT è da applicarsi rullo o pennello come una normale pittura, non necessita diluizione ed è ideale per ambienti domestici, commerciali e ludici.

### APPLICAZIONE

La superficie da decorare con OPACUM ULTRAMATT deve essere opportunamente preparata, secondo quanto segue:

**SU SUPPORTI MURALI NUOVI (STUCCO o MALTA):** per un miglior ancoraggio e per una maggiore durata nel tempo, la superficie deve essere esente da unto o spolvero. Se la superficie è particolarmente ruvida o bucciata, occorre eliminare la ruvidità per agevolare la sensazione tattile ed impedire lo sgradevole fenomeno della 'gessatura'. Applicare a pennello una mano di isolante o fissativo. Dopo minimo 4 ore, applicare OPACUM ULTRAMATT a rullo o pennello, in una o più mani, a seconda delle necessità.

**SU SUPPORTI MURALI GIA' PITTURATI:** con idropitture lavabili: stuccare e carteggiare se necessario; pulire il muro con spugna umida ed applicare una mano a pennello di isolante o fissativo solo sulle stuccature. Se la superficie è particolarmente ruvida o bucciata, occorre eliminare la ruvidità per agevolare la sensazione tattile ed impedire lo sgradevole fenomeno della 'gessatura'. Dopo minimo 4 ore, applicare OPACUM ULTRAMATT a rullo o pennello, in una o più mani, a seconda delle necessità.

**Con tempere, pitture a calce o pitture sfarinanti:** stuccare e carteggiare se necessario; pulire il muro con spugna umida, applicare una mano a pennello di fissativo o isolante su tutta la superficie. Se la superficie è particolarmente ruvida o bucciata, occorre eliminare la ruvidità per agevolare la sensazione tattile ed impedire lo sgradevole fenomeno della 'gessatura'. Dopo minimo 4 ore, applicare OPACUM ULTRAMATT a rullo o pennello, in una o più mani, a seconda delle necessità.

**SU SUPPORTI IN LEGNO NUOVO:** se si vuole mascherare la venatura del legno applicare un fondo per legno ad acqua (Tixtite ad acqua), attendere 12 ore, carteggiare se il caso, sincerandosi di eliminare polvere con panno umido e applicare OPACUM ULTRAMATT a rullo o pennello, in una o più mani, a seconda delle necessità; se si vuole mantenere la naturale venatura del legno applicare direttamente OPACUM ULTRAMATT a rullo o pennello, in una o più mani, a seconda delle necessità. Se la superficie è particolarmente ruvida o bucciata, occorre eliminare la ruvidità per agevolare la sensazione tattile ed impedire lo sgradevole fenomeno della 'gessatura'.



Quality Management System certified ISO 9001: 2015 by Intertek

Prodotto da: **TIXE srl** - 15060 CAPRIATA D'ORBA (AL) ITALY  
Via C. Ferrari, 49 (Frazione Pratalborato) - T. +39 0143 46397  
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992  
**MADE IN ITALY - UN 1263 PAINT**



**SU SUPPORTI IN LEGNO GIA' VERNICIATO:** asportare strati di vernice/smalto che sfogliano o sfarinanti, eliminando unto e polvere, e applicare OPACUM ULTRAMATT a rullo o pennello, in una o più mani, a seconda delle necessità. Se la superficie è particolarmente ruvida o bucciata, occorre eliminare la ruvidità per agevolare la sensazione tattile ed impedire lo sgradevole fenomeno della 'gessatura'.

**SU SUPPORTI METALLICI:** sgrassare e togliere eventuali untuosità, e dopo aver carteggiato, applicare OPACUM ULTRAMATT a rullo o pennello, in una o più mani, a seconda delle necessità.

Applicazioni consigliate: pennello, rullo, spruzzo previa diluizione.

Condizioni dell'ambiente e del supporto:

Il supporto deve essere asciutto, privo di polvere, di unto e di ogni altra sostanza inquinante

Temperatura dell'ambiente: min. 10°C / max

35°C Umidità relativa dell'ambiente: < 75%

Temperatura del supporto: min. 10°C / max 35°C

### **DILUIZIONE**

Il prodotto è pronto all'uso per applicazioni a rullo e pennello, o diluibile a discrezione per migliorare la dilatazione e la penetrazione nel supporto.

Si raccomanda una accurata mescolazione del prodotto prima dell'applicazione, in modo tale da garantire la costante omogeneità del prodotto.

### **STOCCAGGIO**

Conservare il barattolo ben chiuso, al riparo dal gelo e da fonti di calore.

### **CARATTERISTICHE FISICHE** (a 20°C e 50% - 60% U.R.)

|                    |                                 |
|--------------------|---------------------------------|
| Peso specifico     | 1,34 ± 0.05 Kg/l (bianco)       |
|                    | 1.27± 0.05 Kg/l (neutro)        |
| Resa (*)           | 9-10 m <sup>2</sup> /l per mano |
| Viscosità          | 2800-3200 cP Brookfield vel.60  |
| Essiccazione       | 2 ore secco al tatto            |
|                    | 12 ore in profondità            |
| Vita di stoccaggio | Almeno 36 mesi                  |

(\*) La resa dipende dalla natura e dalla porosità della superficie.

### **FORMATO**

Il prodotto è disponibile in formato da 1, 4, 14 litri, in colorazione bianca e base neutra, colorabile a tintometro secondo cartella Colortrend da interno.

### **PRECAUZIONI**

Oltre alle segnalazioni di rischio e precauzione che regolano OPACUM ULTRAMATT nella forma di produzione e che sono riportate sul contenitore, si consiglia, prima di effettuare l'applicazione del prodotto, di consultare la relativa SCHEDA DI SICUREZZA. E' comunque buona norma impiegare guanti ed occhiali di protezione, ed effettuare l'applicazione in ambiente ben aerato.



Quality Management System certified ISO 9001:2015 by Intertek

Prodotto da: **TIXE srl** - 15060 CAPRIATA D'ORBA (AL) ITALY  
Via C. Ferrari, 49 (Frazione Pratalborato) - T. +39 0143 46397  
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992  
**MADE IN ITALY - UN 1263 PAINT**



## Family: DECORATIVE PAINT



## Product: OPACUM ULTRAMATT

### DESCRIPTION

Water-based decorative enamel for interiors with high opacity and highly cleanable.

### MAIN FEATURES

- High opacity
- Excellent washability
- Excellent coverage
- Easy to use
- Wide range of colors

### USE

Water-based decorative enamel with high opacity, designed for the enhancement of furnishings and the personalization of interiors according to the most modern styles and trends. The highly opaque finish gives a uniform and elegant appearance, but at the same time excellent washability and possibility of cleaning, so that even rooms that are particularly frequented and that often require cleaning, can boast finishes with very low light reflection.

The very strong coverage of OPACUM ULTRAMATT and the possibility of coloring in the most varied colors, allow it to be used on the most varied types of surfaces. OPACUM ULTRAMATT is to be applied with a roller or brush like a normal paint, does not require dilution and is ideal for domestic, commercial and play areas.

### APPLICATION

The surface to be decorated with OPACUM ULTRAMATT must be suitably prepared, according to the following:

**ON NEW WALL SUBSTRATES (STUCCO or MORTAR):** for better anchoring and longer life, the surface must be free from grease or dust. If the surface is particularly rough or peeled, it is necessary to eliminate the roughness to facilitate the tactile sensation and prevent the unpleasant 'plastering' phenomenon.

Apply a coat of sealer or fixative with a brush. After at least 4 hours, apply OPACUM ULTRAMATT with a roller or brush, in one or more coats, as needed.

**ON ALREADY PAINTED WALL SUPPORTS:** with washable water-based paints: fill and sand if necessary; clean the wall with a damp sponge and apply a brush coat of sealer or fixative only on the grouting. If the surface is particularly rough or textured, it is necessary to eliminate the roughness to facilitate the tactile sensation and prevent the unpleasant 'plastering' phenomenon. After at least 4 hours, apply OPACUM ULTRAMATT with a roller or brush, in one or more coats, depending on the need.

With tempera, lime paints or powdery paints: fill and sand if necessary; clean the wall with a damp sponge, apply a brush coat of fixative or sealer over the entire surface. If the surface is particularly rough or textured, it is necessary to eliminate the roughness to facilitate the tactile sensation and prevent the unpleasant 'plastering' phenomenon. After at least 4 hours, apply OPACUM ULTRAMATT with a roller or brush, in one or more coats, depending on the need.

**ON NEW WOODEN SUBSTRATES:** if you want to mask the grain of the wood, apply a water-based wood primer (Tixtite water-based), wait 12 hours, sand if necessary, making sure to remove dust with a damp cloth and apply OPACUM ULTRAMATT with a roller or brush, in one or more coats, as needed; if you want to maintain the natural grain of the wood, apply OPACUM ULTRAMATT directly with a roller or brush, in one or more coats, as needed. If the surface is particularly rough or peeled, it is necessary to eliminate the roughness to facilitate the tactile sensation and prevent the unpleasant 'plastering' phenomenon.



Quality Management System certified ISO 9001:2015 by Intertek

Prodotto da: **TIXE srl** - 15060 CAPRIATA D'ORBA (AL) ITALY  
Via C. Ferrari, 49 (Frazione Pratalborato) - T. +39 0143 46397  
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992  
**MADE IN ITALY - UN 1263 PAINT**



**ON ALREADY VARNISHED WOODEN SUPPORTS:** remove layers of paint/enamel that flake or crumble, eliminating grease and dust, and apply OPACUM ULTRAMATT with a roller or brush, in one or more coats, as needed. If the surface is particularly rough or peeled, it is necessary to eliminate the roughness to facilitate the tactile sensation and prevent the unpleasant 'plastering' phenomenon.

**ON METALLIC SUBSTRATES:** degrease and remove any greasiness, and after sanding, apply OPACUM ULTRAMATT by roller or brush, in one or more coats, as needed.

Recommended applications: brush, roller, spray after dilution. Conditions of the environment and support:

The substrate must be dry, free from dust, grease and any other polluting substance

Ambient temperature: min. 10 ° C / max 35 ° C

Relative humidity of the environment: <75%

Temperature of the substrate: min. 10 ° C / max 35 ° C

### **DILUTION**

The product is ready to use for roller and brush applications, or can be diluted at your discretion to improve expansion and penetration into the substrate.

Careful mixing of the product is recommended before application, in order to ensure the constant homogeneity of the product.

### **STORAGE**

Keep the jar tightly closed, away from frost and heat sources.

**PHYSICAL CHARACTERISTICS** (at 20 ° C and 50% - 60% R.H.)

|                 |                                  |
|-----------------|----------------------------------|
| Specific weight | 1.34 ± 0.05 Kg / l (white)       |
|                 | 1.27 ± 0.05 Kg / l (neutral)     |
| Coverage (*)    | 9-10 m <sup>2</sup> / l per coat |
| Viscosity       | 2800-3200 cP Brookfield vel. 60  |
| Drying          | 2 hours dry to the touch         |
|                 | 12 hours in depth                |
| Storage life    | At least 36 months               |

(\*) The yield depends on the nature and porosity of the surface.

### **FORMAT**

The product is available in sizes of 1, 4, 14 liters, in white color and neutral base, which can be colored with a tinting machine according to the Colortrend color chart for interiors.

### **PRECAUTIONS**

In addition to the risk and precautionary warnings that regulate OPACUM ULTRAMATT in the form of production and which are shown on the container, it is advisable, before applying the product, to consult the relevant SAFETY DATA SHEET. However, it is a good idea to use protective gloves and goggles, and apply in a well-ventilated environment



*Quality Management System certified ISO 9001:2015 by Intertek*

Prodotto da: **TIXE srl** - 15060 CAPRIATA D'ORBA (AL) ITALY  
Via C. Ferrari, 49 (Frazione Pratalborato) - T. +39 0143 46397  
www.tixepaint.com - mail@tixepaint.com - P.IVA 01779800992  
**MADE IN ITALY - UN 1263 PAINT**

